

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
12 February 2004 (12.02.2004)

PCT

(10) International Publication Number
WO 2004/013384 A1

(51) International Patent Classification⁷: C30B 15/10

[JP/JP]; 3-2-16 Kitago Honda, Apt. D 101, Takefu-shi,
Fukui 915-0802 (JP). TOGAWA, Takayuki [JP/JP];
Porosupero Meson C0201, 2-20-73 Hiraide Takefu-Shi,
Fukui-Ken, 915-0803 (JP).

(21) International Application Number:
PCT/EP2003/008422

(22) International Filing Date: 30 July 2003 (30.07.2003) (74) Agent: STAUDT, Armin; Edith-Stein-Strasse 22, 63075
Offenbach/Main (DE).

(25) Filing Language: English

(81) Designated States (national): CN, NO, US.

(26) Publication Language: English

(84) Designated States (regional): European patent (AT, BE,
BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU,
IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR).


(30) Priority Data:
2002-223999 31 July 2002 (31.07.2002) JP

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: QUARTZ GLASS CRUCIBLE FOR PULLING UP SILICON SINGLE CRYSTAL AND METHOD FOR PRODUCING THE SAME



WO 2004/013384 A1

(57) Abstract: An object of the invention is to provide a quartz glass crucible reduced in the generation of vibration occurring on the surface of a silicon melt and free from the generation of rough surface and cristobalite spots, yet capable of pulling up single crystal silicon stably and at high yield even in long-term operations; it is also an object to provide a method for producing the same. In a quartz glass crucible for pulling up single crystal silicon comprising a crucible base body having a bottom part and a straight shell part with an inner layer provided to the inner surface thereof, the quartz glass crucible is characterized by that said inner layer comprises a synthetic quartz glass layer from the lowest end to at least a height of 0.25H; a naturally occurring quartz glass layer or a mixed layer of naturally occurring quartz glass and synthetic quartz glass extended in a range of from at least 0.5H to 0.8H; and one selected from a synthetic quartz glass layer, a naturally occurring quartz glass layer, and a mixed quartz glass layer of naturally and synthetic quartz glass for the rest of the inner layer; wherein H represents the height from the lowest end of the bottom part to the upper end plane of the shell part. It also provides a method for producing the quartz glass crucible above.